

# My Company Name

My Address

To: Lexmann Engineering Ltd.  
#105 1301 - 8 Street SW.  
Red Deer, Alberta

Dave Paslawski

Project: ESA Phase III  
Maple Creek Sask.



CERTIFIED LABORATORY FOR TESTING  
CONCRETE IN ACCORDANCE WITH  
STANDARD A283

# Concrete Test Report

Project Number: M99-06-815  
Set Number: 2  
Report Date: AUG.10/99  
Copies To: CLIENT  
Sampled By: EGT/CY  
Tested By: EGT  
Date Cast: JULY.31/99  
Time Cast: 6:35  
Date Received: AUG.2/99

specimen number	date tested	age at test (days)	diameter (mm)	length or span (mm)	Maximum Load (KN)	cross sectional area (mm <sup>2</sup> )	compressive strength (MPa)	failure type	A	X
8217	AUG.7/99	7	151.65	300	407.29	18062.4	22.55	B		
8218	AUG.28/99	28	151.85	300	589.74	18110.0	32.56	C		
8219	AUG.28/99	28	151.75	300	575.19	18086.2	31.80	C		

<u>SPECIFICATIONS</u>	
Specified Strength	25 @ 28 days
Specified Slump	75
Specified Air	5-7
Cement Type	cement type
Cement Content	cement content
Pozzolan Type	pozzolan type
Pozzolan Content	pozzolan content
Admixture	admixture
Max. Agg. Size	28

<u>MEASUREMENTS</u>	
Measured Slump	85 m slump
Measured Air	2.0 mair
Material Temp.	+ 16
Air Temp.	+ 10
Plastic Density	plastic density
Hardened Density	hardened density
<u>CONDITIONS</u>	
Curing Conditions	cure
Initial Curing Temperatures	
Minimum	15min
Maximum	25 max
Mould Type	PLASTIC mould

<u>TICKET INFORMATION</u>	
Supplier	INLAND
Batch Time	5:55 batch time
Truck Number	152 truck
Mix Number	mix number
Ticket Number	03129 ticket
Load Volume	5.5 load
Cummulative Volume	5.5 cumm
Ordered Strength	stren
Ordered Slump	slum
Ordered Air	air
Water Added	water add
Authorized By	authorized by

<u>COMMENTS</u>	
LOCATION:	FLOOR SLAB
WEATHER DESCRIPTION:	this is the wather description
COMMENT:	these are the comments
My Company Name	_____

Reporting of these test results constitutes a testing service only. Engineering interpretation or evaluation of test results is provided only on written request.