

My Company Name

My Address

To: Wall Holdings
 c/o SCHAFFER LTD
 Unit # 4 - 3307 Dunwich Rd. S
 Paris, TN

ATTN: JJ Johnston

Project: Materials Testing
 South Vista - Phase 6

Concrete Test Report

Project Number: M04-04-2599
 Set Number: 3
 Report Date: 09/14/05
 Copies To: CLIENT
 Sampled By: EGT/FK
 Tested By: EGT
 Date Cast: 09/14/05
 Time Cast: 2:30
 Date Received: 17-AUG-04

Specimen	Test Date	Age at Test	Diameter	Length	Max. Load	Area	Strength	Frac. Type	A	B	C	D	E	F
3698	09/21/05	7	101.5	200	222.74	8091.37	27.53	C						
3699	10/12/05	28	101.8	200	267.27	8139.27	32.84	b						
3700	10/12/05	28	101.9	200	275.49	8155.27	33.78	b						

<u>SPECIFICATIONS</u>	
Specified Strength	30 @ 28 days
Specified Slump	40
Specified Air	5.5-7.5
Cement Type	10
Max. Agg. Size	20

<u>MEASUREMENTS</u>	
Measured Slump	30
Measured Air	5.8
Material Temp.	+20
Air Temp.	+28
<u>CONDITIONS</u>	
Initial Curing Temperatures	
Mould Type	100 x 200MM PLASTIC CYLINDER

<u>TICKET INFORMATION</u>	
Supplier	BURNCO
Batch Time	2:01
Truck Number	339 HOWIE
Mix Number	30D5501
Ticket Number	88689
Load Volume	60
Cummulative Volume	108 OF 150

<u>COMMENTS</u>	
LOCATION: LOT 19 BLK 9, SIDEWALK, SOUTHVISTA PHASE 6	
COMMENT: In order to calculate MPa, you must set the Strength factor under the options menu to 1000. Then you can enter loads in Kilonewtons and diameters in Millimeters. Also adjust the column headings in the same option screen for your preference.	
My Company Name _____	