

# My Company Name

My Address

To: LMT Enterprises Ltd.  
P.O. Box 173  
Dunmore, AB.  
T0J 1A0


Kelly Meier

Project: Materials Testing  
McDougal Pit



# Sieve Analysis Report

Project Number: M05-02-3072  
Report Number: 1  
Report Date: 15-Feb-05  
Sample Type: Pit-run  
Sampled By: Client  
Source: McDougal Pit  
Tested By: EGT/ss  
Sample Date: 14-Feb-05  
Date Received: 14-Feb-05  
Date Tested: 15-Feb-05



Sieve Size (mm)	Percent Passing	Percent Retained
200.00	100.000	0.000
150.00	94.831	5.169
125.00	86.801	8.030
100.00	80.505	6.296
75.00	74.210	6.295
50.00	59.343	14.867
40.00	47.306	12.037
25.00	37.593	9.713
20.00	31.981	5.612
12.50	23.229	8.752
10.00	21.336	1.893
5.00	17.982	3.354
2.50	16.115	1.867
1.25	11.108	5.007
0.63	9.967	1.141
0.32	7.892	2.075
0.16	6.266	1.626
0.08	5.614	0.652

FM = 6.0

Pit-run

Per: \_\_\_\_\_